

GRADES

Two grades are usually available in the UK.

- No 2 Clear & Better Only
- No 2 Clear & Better (Allowing Max 15% No 4)

DEFECTS

A broad outline of irregularities permitted within these grades are as follows:

No.2

- Three irregularities on face side per 12ft Length
- Four irregularities on the reverse face per 12ft Length
- Knots up to ½" on face
- Knots up to ¾" on reverse
- 15% of the No.2 grade may contain four irregularities on the face and soft knots.

No.4

- Four irregularities on face side per 12ft Length
- Characteristics on the reverse slightly in excess of those allowed on the face.
- Knots : Four up to 1" or equivalent eg Four 1" or One 4"
- Resin Pockets, Splits, Checks, Warp, Wane and Worm Holes are permitted to some degree.

MOISTURE CONTENT

Western Red Cedar is imported either:

- Kiln Dried (16% Ave with wet spots is Palmers spec)
- Green (No specific moisture content)
- Warning You may also be offered (**Air Dried**) this will have been imported **Green** and termed **Air Dried** because it has been held in stock for a while.

If the term 'Air Dried' is being used as a selling point be sure to ask for a defined moisture content.

Otherwise you may as well specify **Green**.

SPECIFYING THE CORRECT GRADE

As a general rule of thumb the following criteria should be observed.

- **No 2 Clear & Better Only**

Specify this grade if you intend to use specific lengths without joints and you do not wish to do any significant defecting. Eg 100/3.0m lengths used in 3.0m lengths.

- **No 2 Clear & Better (Allowing Max 15% No 4)**

Specify this grade if you intend to use random lengths with random joints in the length and are prepared to defect on site to achieve a clear or nearly clear appearance.

Eg 1000 linier metres supplied in random lengths 1.82m-6.09 metres long.

These guidelines include extracts from BS1186-3 now being quoted as a benchmark quality for claddings in the UK.